

What is claimed is:

1. A titanium oxide having a selected ion chromatogram in which an evolution gas having 28 of a ratio of mass number to electric charge quantity exhibits at least one peak at
5 about 600°C or higher, the selected ion chromatogram being measured in a thermogravimetry-mass-spectroscopy.

2. The titanium oxide according to claim 1, further having a selected ion chromatogram in which an evolution gas having 14 of a ratio of mass number to electric charge quantity
10 exhibits a peak at about 600°C or higher, the selected ion chromatogram being measured in a thermogravimetry-mass-spectroscopy.

3. The titanium oxide according to claim 1, wherein said pack of the evolution gas having 28 of a ratio of mass
15 number to electric charge quantity is exhibited at about 950°C or lower.

4. The titanium oxide according to claim 2, wherein said pack of the evolution gas having 14 of a ratio of mass
20 number to electric charge quantity is exhibited at about 950°C or lower.

5. The titanium oxide according to claim 1, further having a selected ion chromatogram in which an evolution gas having 64 of a ratio of mass number to electric charge quantity exhibits a peak at about 400°C or higher, the selected ion
25 chromatogram being measured in a

thermogravimetry-mass-spectroscopy.

6. The titanium oxide according to any one of claims
1 to 5, wherein the selected ion chromatogram is measured
under a condition of applying a Channeltron Electron
Multiplier voltage of 1000V.

7. The titanium oxide according to any one of claims
1 to 5, wherein the selected ion chromatogram is measured
under a condition of applying a Channeltron Electron
Multiplier voltage of 1500V.

8. A photocatalyst containing the titanium oxide as
claimed in any one of claims 1 to 5 as a catalyst component.

9. A photocatalyst coating composition comprising the
titanium oxide as claimed in any one of claims 1 to 5 and
a solvent.